

best wood FLOOR 160

Version 02/2026



Wood fiber insulation board with foundation lath to fasten floor structures. Wood fiber insulation board without foundation lath for application as sub-base for floating dry screed structures as well as self levelling floor screeds and cement screeds. Foundation lath from spruce with tongue and groove.

Technical information

Denomination	WF-EN 13171-T5-CS(10\Y)150-TR25-WS1, 0-MU5-AF75-SD60-CP2
Norm	EN13171
Density	160 [kg/m ³]
Nominal value of thermal conductivity λ_D	0.041 [W/(mK)]
Rated value of thermal conductivity λ	0.043 [W/(mK)]
Reaction to fire according to DIN EN 13501	E
Construction material class according to DIN 4102	B2
Full declaration	Wood fibers, PMDI gluing, paraffin
Production process	Dry process
Compressive stress at 10% compression	≥ 150 [kPa]
Tensile strength perpendicular to the plane of the board	≥ 25 [kPa]
Modulus of elasticity $E_{(d)}$	≥ 1.45 [N/mm ²]
Water vapor diffusion resistance μ	5
Linear flow resistance	> 75 [kPa·s/m ²]
Short time water absorption	< 1.0 [kg/m ²]
Specific heat capacity	2,100 [J/(kg K)]
Waste code according to AVV	030105, 170201

Fields of application according to DIN 4108-10

DEO-ds

DEO Inside insulation of the ceiling (on the top) under screed without noise protection requirements

ds High pressure resistance



Delivery formats insulation board

Edge formats	Tongue + groove
Thickness	40, 60, 80 mm
Length	1,500 mm
Width	580 mm
Pallet height	up to a max. of 1,350

Delivery formats foundation lath from spruce

Edge formats	Tongue + groove
Thickness	35 mm
Length	2,000 mm
Width	50 mm cover size; 60 mm profile size

Board weights

Thickness in mm	1 m ²	580 x 1,500 mm 0.87 m ²
40	6,4 kg	5,6 kg
60	9,6 kg	8,4 kg
80	12,8 kg	11,2 kg

Certificats



Installation advice

- Store and install FLOOR 160 dry
- Install the boards laterally, exact and without joints
- Cut with a common woodworking tool
- Diagonal joints are not allowed
- Do not install damaged boards!
- For acoustic decoupling, FLOOR 160 and foundation lath must not be installed with contact to the wall
- Dust extraction in accordance with BG regulations
- Installation elements or inlets (e.g. solar pipes ...), for which temperatures of > 80°C can be expected, must not be installed without any additional fire precautions into the best wood SCHNEIDER® wood fiber insulation materials.

Please note that a structural calculation has to be done before installation. The present tables are only including guide values. All rights reserved. The technical data provided herein is subject to change. Although all of the information herein was up to date at the time of its publication, the publication of superseding information renders the old information invalid. Regional and national regulations and building law have to be fulfilled. The suitability and the details have to be checked for the intended use. best wood SCHNEIDER® GmbH shall not be held liable for any damage resulting from error or misprinting.

