

Bonding and sealing

SOLITEX FRONTA WA

3-ply wall lining membrane with monolithic TEEE membrane, suitable for closed facades.

Application

To make walls externally windproof. Installation on boarding, wood-based panels and all insulation mats and boards.

Advantages

Strong, 3-ply structure to protect the wall structure; protective function as a result of non-porous functional membrane that actively manages moisture; high nail tear resistance; for application behind closed facades; 3 months outdoor exposure.

Please note:

Due to normative requirements concerning the UV stability, the Solitex Fronta WA can no longer be used behind complete formwork. Therefore, pro clima recommends Solitex Fronta Quattro for complete formworks.



13
DIN EN 13859-2



developed and produced by pro clima

Protection and cover fleece	Polypropylene microfiber
Membrane	Monolithic TEEE film
Thickness	0.45 ± 0.05 mm
s _d -value	0.05 ± 0.02 m
Fire rating	E
Outdoor weather exposure	3 months
Water column	10,000 mm
Surface weight	100 ± 5 g/m ²
Temperature resistance	- 40°C to + 100°C
Tensile strength longitudinal/ transverse	210 ± 20 N/5 cm / 140 ± 20 N/5 cm

Item no.	Roll length	Roll width	Area	Roll weight		
6101SOLITEXFRONTAWA150	50 m	1.50 m	75 m ²	7.5 kg		